

## CIRCULUM®

### B-980p

#### DESCRIPTION

**B-980p** is an expandable polystyrene grade containing pentane as a blowing agent. The product is delivered in the form of spherical beads with a bulk density of about 0.6 g/cm<sup>3</sup> and is available in 1100 kg octabins.

#### APPLICATIONS

The properties of **B-980p** make it suitable for the production of shape moulded products with densities higher than 18 kg/m<sup>3</sup>.

#### PROCESSING

The processing conditions of **B-980p** depend on the combination of the product and processing equipment used. Optimal settings have to be adjusted for each combination. Some general processing conditions are given below:

<b>Prefoaming</b>	The steam has to be saturated at a temperature of 100–110 °C. For higher densities (> 30 kg/m <sup>3</sup> ) it is recommended to mix the steam with air.
<b>Conditioning</b>	Depends on the density. The higher the density the longer the conditioning time. Generally 12–24 hours is recommended.
<b>Moulding</b>	The machine should be fed with saturated steam with a max pressure of about 2 bar.
	The steaming time depends on the equipment used as well as the size and required strength of the final product. Therefore, all machines have to be adjusted individually. Equipment using vacuum is recommended to reduce cycle times and to increase product strength.
<b>Cutting</b>	Hot wire cutting (oscillating or stationary wires) is recommended. Temperature of the wires should be about 200–300 °C.

### TECHNICAL INFORMATION

#### TYPICAL PHYSICAL PROPERTIES

Raw material	Value	Unit	Test method
Pentane content	5.5 – 6.5	%	Gas chromatography
Monomer level	< 0.1	%	Gas chromatography
Main bead size distribution	0.4 – 0.7	mm	Image analyser
End product			
	<u>20 kg/m<sup>3</sup></u>	<u>30 kg/m<sup>3</sup></u>	<u>40 kg/m<sup>3</sup></u>
Compressive stress (10 %), (kPa) EN 826	120	200	280
Bending strength, (kPa) EN 12089	240	380	560
Heat conductivity ( $\lambda_{10}$ ), (W/mK) EN 12667	0.034	0.032	0.032

#### FOOD CONTACT REGULATIONS

**B-980p** meets the food contact regulations in most countries. If required, contact your BEWI representative for a certificate.

#### STORAGE

**B-980p** should be stored at below 20 °C. Protect from direct sunlight and other weather conditions (rain, wind, frost etc.). Keep away from any source of ignition. The storage time should not exceed three months. After opening of the packaging, it should be used as soon as possible.

#### SAFETY

In transport **B-980p** is classified according to European regulations for product transport: Substance number UN2211, Class 9.

In processing avoid generating dust. All equipment should be properly earthen. Releases pentane during processing which might form a flammable/explosive vapour-air mixture. Use proper ventilation and keep away from any source of ignition. A Safety Data Sheet is available on request.

#### RECYCLING

**B-980p** is suitable for recycling using modern methods of grinding, cleaning and regranulation. In-house production waste should be kept clean to facilitate direct recycling.

Please contact your BEWI representative for more details on various aspects of safety, recovery and disposal of the product.

This information is not to be taken as a warranty or representation for which BEWI Oy assumes legal responsibility nor as permission or recommendation to practice any patented invention without a license. It is offered solely for your consideration, investigation, verification and shall form no part of any contract with a customer.

La présente documentation n'engage pas notre responsabilité et n'autorise en aucune façon l'usage sans contrat de licence d'inventions brevetées. Les termes du présent rapport doivent être considérés comme une simple indication, sujette aux vérifications d'usage.

Bei diesen Angaben handelt es sich weder um eine Garantie-Erklärung oder Darstellung, für die wir eine rechtliche Haftung übernehmen, noch um eine Erlaubnis oder Empfehlung, irgendeine patentierte Erfindung ohne Lizenz auszuwerten. Die Informationen werden Ihnen lediglich zu Ihrer Erwägung, Untersuchung und Überprüfung übermittelt und sind nicht Bestandteil von Verträgen mit Kunden.

Uppgifter i datablad, broschyrer och annat informationsmaterial ges som vägledning och är ej bindande för BEWI Oy.

Tässä esitteessä ja muussa tiedotusaineistossa annetut tekniset tiedot ovat suuntaan antavia, eivätkä ne ole BEWI Oy:tä sitovia.

Le informazioni contenute nelle schede tecniche, bollettini ed altro materiale informativo corrispondono all'attuale livello di conoscenza e intendono fornire indicazioni sui prodotti BEWI Oy e le loro possibilità di impiego. Non sono pertanto da intendersi come garanzia.