

CIRCULUM®

BIOFOAM

DESCRIPTION

BioFoam is an expanded poly lactic acid foamed bead

The products are delivered in the form of spherical beads with a bulk density between 16-250 g/L.

BioFoam is available in 1.8m³ big bags.

APPLICATIONS

The properties of **BioFoam** make it suitable for filling hollow spaces, beanbags, pillows and for the production of light and heavy products by shape moulding.

PROCESSING

The processing conditions of **BioFoam** depend on the combination of the product and processing equipment used. Optimal settings have to be adjusted for each combination. Some general processing conditions are given below:

Prefoaming

Before prefoaming the beads need to be impregnated with CO₂ in a pressure vessel. The impregnated beads can be foamed with hot air or a mixture of steam with air.

Coating

For the foamed beads to continue to the molding step a coating must be applied to improve the fusion between the beads.

Moulding

Prior to molding the foamed beads need to be impregnated with air or pressure filling must be applied because no blowing agent is inside the beads.

The machine should be fed with saturated steam with a maximum pressure of about 2 bar.

The steaming time depends on the equipment used as well as the size and required strength of the final product. Therefore, all machines have to be adjusted individually. Equipment using vacuum is recommended to reduce cycle times and to increase product strength.

Cutting

Hot wire cutting (oscillating or stationary wires) is recommended. Temperature of the wires should be about 200–300 °C.

TECHNICAL INFORMATION

TYPICAL PHYSICAL PROPERTIES

Raw material

	<u>Value</u>	<u>Unit</u>	<u>Test method</u>
Monomer level	< 0.1	%	Gas chromatography
Main bead size distribution	0.8 – 1.6	mm	Image analyser

End product

Compressive stress (10 %), (kPa), EN 826		35 <u>kg/m³</u>	160
Bending strength, (kPa), EN 12089			250
Heat conductivity (λ_{10}), (W/mK), EN 12667			0.035

SHRINKAGE

Above 50°C there is a possibility that the Biofoam parts will shrink.

STORAGE

BioFoam should be stored at below 30 °C. Protect from direct sunlight and other weather conditions (rain, wind, frost etc.). The storage time should not exceed one year.

SAFETY

In transport **BioFoam** is classified according to European regulations for product transport: non hazardous.

RECYCLING

BioFoam is suitable for recycling using modern methods of grinding, cleaning and regranulation. In-house production waste should be kept clean to facilitate direct recycling.

Please contact your BEWi RAW representative for more details on various aspects of safety, recovery and disposal of the product.

This information is not to be taken as a warranty or representation for which BEWi RAW assumes legal responsibility nor as permission or recommendation to practice any patented invention without a license. It is offered solely for your consideration, investigation, verification and shall form no part of any contract with a customer.

La présente documentation n'engage pas notre responsabilité et n'autorise en aucune façon l'usage sans contrat de licence d'inventions brevetées. Les termes du présent rapport doivent être considérés comme une simple indication, sujette aux vérifications d'usage.

Bei diesen Angaben handelt es sich weder um eine Garantie-Erklärung oder Darstellung, für die wir eine rechtliche Haftung übernehmen, noch um eine Erlaubnis oder Empfehlung, irgendeine patentierte Erfindung ohne Lizenz auszuwerten. Die Informationen werden Ihnen lediglich zu Ihrer Erwägung, Untersuchung und Überprüfung übermittelt und sind nicht Bestandteil von Verträgen mit Kunden.

Uppgifter i datablad, broschyrer och annat informationsmaterial ges som vägledning och är ej bindande för BEWi RAW.

Tässä esitteessä ja muussa tiedotusaineistossa annetut tekniset tiedot ovat suuntaa antavia, eivätkä ne ole BEWi RAW:tä sitovia.

Le informazioni contenute nelle schede tecniche, bollettini ed altro materiale informativo corrispondono all'attuale livello di conoscenza e intendono fornire indicazioni sui prodotti BEWi RAW e le loro possibilità di impiego. Non sono pertanto da intendersi come garanzia.